

DERWENT

# Inktense Blocks

Vibrant strokes of ink-like colour

	LF		LF
 0100 Sherbet Lemon	●●●● 8	 1210 Dark Aquamarine	●● 8
 0200 Sun Yellow	●●●● 8	 1215 Turquoise	●●● 8
 0210 Cadmium Yellow	●●● 7	 1220 Green Aquamarine	●●● 8
 0220 Sicilian Yellow	●●● 8	 1230 Mallard Green	●●● 8
 0230 Golden Yellow	●●● 7	 1300 Teal Green	●●●● 8
 0240 Sienna Gold	●●● 6	 1310 Iron Green	●●● 8
 0250 Cadmium Orange	●●● 7	 1320 Ionian Green	●●● 8
 0260 Burnt Orange	●●● 6	 1330 Vivid Green	●●● 7
 0300 Tangerine	●●●● 7	 1400 Apple Green	●●●● 8
 0310 Mid Vermilion	●●● 7	 1500 Field Green	●●● 7
 0320 Scarlet Pink	●●● 7	 1510 Beech Green	●●● 7
 0400 Poppy Red	●●●● 7	 1520 Hooker's Green	●●● 8
 0410 Hot Red	●●● 7	 1530 Felt Green	●●● 7
 0500 Chilli Red	●●● 7	 1540 Light Olive	●●● 7
 0510 Cherry	●●● 6	 1550 Spring Green	●●● 7
 0520 Carmine Pink	●●● 7	 1560 Fern	●●● 8
 0530 Crimson	●●● 5/6	 1600 Leaf Green	●●●● 8
 0600 Shiraz	●●● 4/5	 1700 Mustard	●●● 6
 0610 Red Violet	●●● 6	 1710 Amber	●●● 8
 0700 Fuchsia	●●●● 7	 1720 Tan	●●● 7
 0710 Deep Rose	●●● 7	 1730 Oak	●●● 8
 0720 Thistle	●●● 6/7	 1740 Saddle Brown	●●● 8
 0730 Dusky Purple	●●● 7	 1800 Baked Earth	●●●● 8
 0740 Mauve	●●● 7	 1900 Willow	●●● 8
 0750 Dark Purple	●●● 7	 1910 Red Oxide	●●● 8
 0760 Deep Violet	●●● 6	 1920 Madder Brown	●●● 8
 0800 Violet	●●● 7	 1930 Dark Chocolate	●●● 7
 0810 Lagoon	●●● 7	 2000 Bark	●●●● 8
 0820 Peacock Blue	●●● 7	 2010 Sepia Ink	●●● 8
 0830 Navy Blue	●●● 7	 2020 Indian Ink	●●● 8
 0840 Iron Blue	●●● 8	 2030 Chinese Ink	●●● 8
 0850 Deep Blue	●●● 7/8	 2100 Charcoal Grey	●●● 7
 0900 Iris Blue	●●● 7	 2110 Payne's Grey	●●● 8
 1000 Bright Blue	●●● 7	 2120 Neutral Grey	●●● 8
 1100 Deep Indigo	●●●● 7	 2200 Ink Black	●●●● 8
 1200 Sea Blue	●●●● 7	 2300 Antique White	●●● 8

● tin of 12 ● tin of 24 ● tin of 36 ● tin of 72

Please note that the contents may be substituted at any time with a product equal or superior to that specified.

LF - Lightfastness rating

Lightfastness refers to the chemical stability of a pigment under long exposure to light. Light can cause colour to whiten, darken, fade or completely disappear.

The Blue Wool Scale - two pieces of blue wool are used to test lightfastness. One is placed in the dark and the other in the equivalent of sunlight for a period of three months. After three months the two pieces of wool are compared and rated between 0 - 8. 8 is the highest rating and values of 6 or higher are considered to be lightfast.